



Incorporated 1920

Underwriters' Laboratories of Canada

An Affiliate of Underwriters Laboratories Inc.

R20971
02NK24744

August 16, 2002

Mr. Charlie Cooper
President
Pyrologistix
1645 Howe Island Drive
Howe Island, ON
K7G 2V6

Subject: Surface Burning Characteristics of Coatings

Dear Charlie:

On August 12, 2002, a fire test was conducted at Underwriters' Laboratories of Canada in Toronto, in accordance with the Standard CAN/ULC-S102-M88, Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies, on a coating described by the client as "Pyrologistix Contego Fire Barrier Intumescent Paint (F.B.I. Paint)".

The coating was applied in two coats to Douglas Fir decks, under the observation of a ULC representative, on July 30, 2002. The first coat was applied at a rate of 3.2 m²/L (130 ft²/gal). The second coat was applied at a rate of 3.9 m²/L (160 ft²/gal), (1 gal = 3.78 L).

The results were as follows:

<u>Coating</u>	<u>Flame Spread</u>	<u>Smoke Developed</u>
F.B.I. Paint	0	0

HEAD OFFICE AND TESTING STATION:
7 Crouse Road, Toronto, Ontario, Canada M1R 3A9
Telephone: (416) 757-3611 or 1-800-INFO-ULC
Fax: (416) 757-8915
Visit us at: www.ulc.ca e-mail: ulcinfo@ulc.ca

